

TECHNICAL INFORMATION DISEGNA BASTONE

Profile 120mm square section side

TEST	STANDARD	VALUE	STANDARD DESVIATION
Apparent Density (kg/m ³)	UNE EN 323	323	1
Density (kg/m ³)	UNE EN 323	1196	3
Bending Resistance (N/mm ²) · Longitudinal	UNE EN 310	5,90	0,39
Elasticity Resistance (N/mm ²) · Longitudinal	UNE EN 310	400	40
Swelling of thickness after immersion in water 24 hours (%)	UNE EN 317	Side 1: 0,053 Side 2: 0,058	0,005
Absorption of thickness after immersion in water 24 hours (%)	UNE EN 317	2,61	0,1
Brinell Hardness(N/mm ²)	UNE EN 1534	52,2	10
Lineal thermal contraction (mm/m)	UNE EN 15534	5,0	0,4
Expansion coefficient (mm/m °C)	UNE EN 15534	0,0635	0,0015

Tests made by AIDIMA. AIDIMA is an accredited lab by ENAC in Spain.
www.aidima.es www.enac.es

TechInf V1

Disegna® is a brand of the Condepols® group. A group of companies with over 50 years' experience developing and manufacturing polymer products. Disegna® sell their products in over 60 countries and are focused on developing and manufacturing products with a high added value while remaining environmentally sustainable.